

FAIR Plastic /02 – Datasheet

Polypropylene/Polyetylene " PP/PE 70/30 black" Reprocessed pellets
This material can be modified according to the customer's wishes

This PP/PE is reprocessed from colored washed postconsumer plastic.
The data should be regarded as indicative and should not be used for specification work.
Ragn Sells A/S assumes no legal responsibility for the precision or correctness of the test results.

Color:	Black			
MFR	(230 °C: 2,16 kg)	9,0	g/10min	ISO1133*
Charpy impact strength	notch (+23°C)	7,7	Kj/m ²	ISO 179/1eA*
Tensile stress at yield	(50 mm/min: +23 °C)	26	Mpa	ISO 527-1-2*
Tensile stress at break	(50 mm/min: +23 °C)	26	Mpa	ISO 527-1-2*
Elongation at break	(50 mm/min: +23 °C)	10	%	ISO 527-1-2*
E – mod	(1 mm/min: + 23 °C)	1086	Mpa	ISO 527-1-2*

Screening:	200 Micron / 70 Mesh
Use:	Injection
Packaging:	1.000 kg Big Bags

Ragn-Sells Danmark A/S
Maglemølle 46
DK-4700 Næstved
Phone: +45 70702555-2

*Test results are based on the relevant standard as guideline.
Verifying document date: 04-12-2018

